



Falcon Silicone Roof Coating

Physical Properties & Specifications

Weight per Gallons:	11.1 Lbs.
Solids by Weight:	>96%
Solids by Volume:	>97%
Color:	White
Elongation:	270%, Nominal
Tensile Strength:	300 PSI, Nominal
Tear Resistance:	35 Lbs. Force/in. ASTM D 624
Hardness, Shore A:	50
Cure Time:	2 - 6 hours hours at 77° F and 50% relative humidity
Packaging:	Drum, 5 & 1 gallon pail
Application Temperature:	40° F to 120° F
Service Temperature (Cured Film):	-40° F to 300° F
VOC Content:	<50 g/L

For use information please refer to product label