



Artemis 2 - 100% Acrylic High Performance Roof Coating

Physical Properties & Specifications

Weight per Gallons:	11.8 Lbs.
Solids by Weight:	60%, Nominal
Solids by Volume:	53%, Nominal
Color:	White
Elongation:	250%, Nominal
Tensile Strength:	300 PSI, Nominal
Tear Resistance:	82 Lbs. Force/in. ASTM D 624
Hardness, Shore A:	70
Cure Time:	24 to 48 hours at 77° F and 50% relative humidity
Packaging:	Tote, Drum, 5 & 1 gallon pail
Application Temperature:	40° F to 120° F
Service Temperature (Cured Film):	15° F to 180° F
VOC Content:	50 g/L

For use information please refer to product label