



**Artemis 1 - Elastomeric Roof Coating**

*Physical Properties & Specifications*

Weight per Gallon:	8.3 Lbs/gallon
Solids by Weight:	44%, Nominal
Solids by Volume:	55%, Nominal
Color:	White
Elongation:	210%, Nominal
Tensile Strength:	200 PSI, Nominal
Cure Time:	24 to 48 hours at 77 ° F and 50% relative humidity
Packaging:	Tote, Drum, 5 & 1 gallon pail
Application Temperature	40 ° F to 120 ° F
Service Temperature (Cured Film):	15 ° F to 180 ° F
VOC Content:	50 g/L

For use information please refer to product label